

Prirodna koža za namještaj

<u>Test</u>	<u>Method</u>	<u>Min. recommended value</u>
DRY RUBBING - 500 Cycles	EN ISO 11640	> 4 grey scale
WET RUBBING - 250 Cycles	EN ISO 11640	> 3/4 grey scale
PERSPIRATION RUBBING - 80 Cycles	EN ISO 11640	> 3/4 grey scale
FINISH ADHESION	EN ISO 11644	> 2 Newton/cm
FLEXING ENDURANCE - 50.000 Cycles	EN ISO 5402	No surface damage or cracks
COLOUR FASTNESS TO LIGHT	EN ISO 105-B02	> 5 Blue scale
TEAR STRENGTH	EN ISO 3377-1	> 20 Newton
pH AND ΔpH	EN ISO 4045	> 3,2; if < 4, ΔpH < / = 0,7